

The effect of moisture on continuous polymerization of thermoplastic polyurethane (TPU)

Reporter: Xin Liu^a

Junying Zhang^a ,Lutong Gan^b ,Kunhuan Liang^b ,Pengpeng Sheng^b Beijing University of Chemical Technology^a Jiangmen YingChuan Polyurethane material CO. ,LTD. ^b

Date: 9.17. 2012









TPU

the continuity of the reaction process

- **Batch Method**
- Poor repeatability
- Unstable performance
- Difficulties in late granulation

- Continuous Method
- Good repeatability
- Stable performance
- High production efficiency



Reaction Principle

Process Technique

Measurement

Conveying


Mixing

Reaction

Extruding

Pelletizing






- Accurate measurement
- Uniform mixing
- Fixed reaction time and temperature
- High quality



Background

Influence Factors





1. Synthesis

C_{h}	Num.	Wd (g)	Wi (g)	Wg (g)	H ₂ O(ppm)
20%	1#	0.03	12.4	50	0
	2#	0.03	12.4	50	200
	3#	0.03	12.4	50	400
	4#	0.03	12.4	50	600

Note: Ch is the hard segment content; Wd is the quality of BDO; Wi is the quality of MDI; Wg is the quality of PBA.



2.1 The effect of water content on TPU physical parameters

Number	Shore Hardness/A	Ring and Ball Softening Point/°C	MI/120°C、2.16kg
1#	75	115	8.5
2#	75	95	9
3#	75	89	22
4#	75	85	34

 $H_2O \longleftrightarrow H-O-H \longleftrightarrow R \text{ value} \longleftrightarrow Mn$



2.2 The effect of moisture on TPU structure




Fig. 1. FTIR spectrum of TPU in defferent temperature.



2.3 The effect of water content on Mn of TPU




Fig. 2. The relationship of water content and TPU Mn.

Conclusion

- 1. Water plays as extender in the process of continuous polymerization of TPU;
- 2. With the increase of water content, the softening point decreased, and the MI increased.

Fisheyes exist in the process, which are unexplained so far, still needs further research



THANKS